

## TB - L (Micro) >> COATED

Brown Fused Aluminum Oxide

TB is a friable brown fused aluminum oxide obtained from the fusion of high purity bauxites in electric arc furnaces. It presents an excellent cost/benefit ratio, being recommended for wood and dry wall coated abrasives.

### General Characteristics

True Specific Gravity
3,96 g/cm <sup>3</sup>

### Chemical Analysis by XRF (%)

Al <sub>2</sub> O <sub>3</sub>	TiO <sub>2</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	MgO
95,52	1,98	0,97	0,83	0,29

### Grit Sizes

Grit	Ds 0 (%)	Ds 3 (%)	Ds 50 (%)		Ds 95 (%)
	Maximum	Minimum	Minimum	Maximum	Minimum
240	110,0	81,7	56,5	60,5	44,5
280	101,0	74,0	50,2	54,2	39,2
320	94,0	66,8	44,7	47,7	34,2
360	87,0	60,3	39,0	42,0	29,6
400	81,0	53,9	33,5	36,5	25,2
500	77,0	48,3	28,7	31,7	21,5
600	72,0	43,0	24,8	26,8	18,0
800	67,0	38,1	20,8	22,8	15,1

FEPA 43 - 2:2006

\* Other grit sizes upon request.